

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
16 December 2004 (16.12.2004)

PCT

(10) International Publication Number
WO 2004/108312 A1

(51) International Patent Classification⁷: **B21B 27/10**

(21) International Application Number:
PCT/JP2004/008152

(22) International Filing Date: 4 June 2004 (04.06.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2003-162490 6 June 2003 (06.06.2003) JP

(71) Applicant (for all designated States except US): NIPPON STEEL CORPORATION [JP/JP]; 6-3, Otemachi 2-chome, Chiyoda-ku, Tokyo 1008071 (JP).

(72) Inventor; and

(75) Inventor/Applicant (for US only): INOUE, Tsuyoshi [JP/JP]; C/o Nippon Steel Corporation Technical Development Bureau, 20-1 Shintomi, Futtsu-shi, Chiba 2938511 (JP).


(74) Agent: KOKUBUN, Takayoshi; 5th Floor, Ikebukuro TG Homest Building, 17-8, Higashi-Ikebukuro 1-chome, Toshima-ku, Tokyo 1700013 (JP).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: LUBRICATED HOT ROLLING METHOD



(57) Abstract: In a lubricated hot rolling method using a lubricating oil which contains one kind or two or more kinds among an high-basic alkaline-earth metal phenate, high-basic alkaline-earth metal carboxylate, high-basic alkaline-earth salicylate, or high-basic alkaline-earth metal sulfonate having a basicity of 40 mgKOH/g or higher, and has a viscosity at 40 C of 800 cSt or less, rolling is performed by granulating or atomizing the lubricating oil into particulates whose average size is less than 1 mm, supplying it to rolls by using a noncombustible gas whose flow rate is 2000 cm³/s or more per minute per lubricating nozzle and whose velocity is 1 m or more per second, and controlling the amount supplied of the lubricating oil to 0.01 cm³/s or more and 20 cm³/s or less per 1 m² of a surface area of the rolls.

BEST AVAILABLE COPY

WO 2004/108312 A1



Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

BEST AVAILABLE COPY

BEST AVAILABLE COPY